

Technical Data Sheet

B8115

Fabric / Weefsel / Tissu / Gewebe	100 % PES / 1100 dtex	
Total weight / Gewicht totaal / Poids total / Totalgewicht	850 g/m ²	DIN EN ISO 2286/2 1998
Embossing / Kalander / Calandre / Lackierung	Dull/LIN	
Characteristics Eigenschappen Caractéristiques Eigenschaften	ABUV / SOP	
Lacquering / Vernis / Lackierung	1/1	
Comment / Opmerking / Remarque / Kommentar	Non-marking dull lacquer	
Breaking strength Warp Treksterkte Ketting Résistance rupture Chaîne Höchstzugkraft Kette	2500 N/5cm	EN ISO 1421/1 1998
Breaking strength Weft Treksterkte Inslag Résistance rupture Trame Höchstzugkraft Schuss	2300 N/5cm	EN ISO 1421/1 1998
Tear strength Warp Scheurweerstand Ketting Résistance à la déchirure Chaîne Weiterreisskraft Kette	270 N	DIN 53363 2003
Tear strength Weft Scheurweerstand Inslag Résistance à la déchirure Trame Weiterreisskraft Schuss	270 N	DIN 53363 2003
Adhesion / Hechting / Adhérence / Haftung	100 N/5cm	EN ISO 2411 2000

"This product may for certain colours contain substances (Lead Pigments) which fall under the Annex XIV of the Reach Regulation 1907/2006/CE.
In order to know which colours fall under this annex , you can take contact with the technical department of Sioen Industries.
Upon request those substances can be eliminated from the product."

Technical Data Sheet

B8115

Temperature resistance / Temperatuursbestendigheid / Tenue à la température / Temperatuursbestendigheid	-30/+70 °C	DIN EN 1876/2 1998
Light fastness (Except white and (half-)transparent)	7-8	ISO 105 B02 2014
Lichtechtheid (Uitgezonderd wit en (half-)transparent)		
Tenue à la lumière (Excepté en blanc et (semi-)transparent)		
Lichtechtheit (Ausnahme weiss und (semi-)transparent)		
Fire behavior / Brandgedrag / Reaction au feu / Brennverhalten	ADR classe II	UNI 8456 - UNI 9174
Application -> Tent&TA/BlockOut		

"This product may for certain colours contain substances (Lead Pigments) which fall under the Annex XIV of the Reach Regulation 1907/2006/CE. In order to know which colours fall under this annex , you can take contact with the technical department of Sioen Industries. Upon request those substances can be eliminated from the product."